Product Data Sheet

Edition: 7/2008 Version no.: 0006

Sikaplan® 60

Composition:	Sikaplan [®] 60 is a white, 60 mil. nominal, PVC membrane. Sikaplan 60 is manufactured with a polyester scrim for reinforcement. Sikaplan 60 meets the cool roofing requirements of California's Title 24, USGBC's LEED [®] program and Green Globes. The membrane meets init Energy Star [®] Reflectivity Requirements with an initial solar reflectance of 0.81 an initial solar emmitance of 0.85 and a SRI of 101. Three year, age membrane reflectivity testing results are pending.			
Features:				
Packaging:	Sikaplan 60 comes in 10 feet x 100 feet rolls weighing approx. 360 lbs and 5 feet x 100 feet rolls weighing approx. 180 lbs. Sikaplan 60 membrane is wrapped in a clear protective film and strapped 8 rolls to a wooden pallet.			
Installation:	Sikaplan 60 is installed by a Sika Sarnafil Authorized Applicator. Sikaplan 60 shall be installed to an acceptable substrate with fasteners and plates in the seam overlap in the "Sikaplan Mechanically-Attached System". All seams will be hot-air welded for watertight protection. Sikaplan 60 can be used on flashings on Sikaplan roof assemblies.			
Availability:	Sikaplan 60 is available directly from a Sika Sarnafil Authorized Applicator or by contacting your Sika Sarnafil regional office. For office locations please contact Sika Sarnafil.			
Warranty:	Upon successful completion of the installed roof by the Sika Sarnafil Authorized Applicator, Sika Sarnafil will provide a warranty to the building owner via the applicator.			
Maintenance:	Sikaplan 60 requires no maintenance. As a prudent preventative measure, Sika Sarnafil recommends that the building owner or owner's representative inspect the installed roof system for damage, plugged drains, weathered sealants, etc. at least twice a year and after each storm.			





Technical:

Sika Sarnafil's Technical Representatives are available to advise applicators as to the correct installation methods of Sikaplan 60.

Technical Data (as manufactured):

<u>Parameters</u>	ASTM <u>Test Method</u>	ASTM D-4434 Spec. <u>Requirement</u>	Typical Physical <u>Properties</u>
Reinforcing Material			Polyester
Overall Thickness, min. Thickness Over Scrim	D751 D751	0.045 (1.14)	0.060 (nominal) 0.026 (avg.)
Breaking Strength, min., lbf/in. (KN/m)	D751	200 (35.0)	303 (53.1)
Elongation at Break, min.	D751		(0011)
Machine Direction		15%	42%
Cross Direction		15%	47%
Seam Strength, min., (% of breaking strength)	D751	75	85
Retention of Properties After Heat Aging	D3045		
Tensile Strength, min., (% of original)	D751	90	95
Elongation, min., (% of original)	D751	90	90
Tearing Strength, min., lbf (N)	D1004	45.0 (200)	50 (220.0)
Low Temperature Bend, -40 °F (-40 °C)	D2136	Pass	Pass
Accelerated Weathering Test (Florescent Light, UV expos	ure) G154	5,000 Hours	10,000 Hours
Cracking (7x magnification)		None	None
Discoloration (by observation)		Negligible	Negligible
Crazing (7x magnification)		None	None
Linear Dimensional Change	D1204	0.5% max.	0.24%
Weight Change After Immersion in Water	D570	± 3.0% max.	2.5%
Static Puncture Resistance, 33 lbf (15 kg)	D5602	Pass	Pass
Dynamic Puncture Resistance, 14.7 ft-lbf (20 J)	D5635	Pass	Pass
Initial Solar Reflectance	E903		0.81
Emissivity E	E408, C1371, Other		0.85
Solar Reflective Index (SRI)	E1980		101

Corporate Office

Sika Sarnafil A Division of Sika Corporation 100 Dan Road Canton, MA 02021

Tel.: (781) 828-5400 1-800-451-2504 Fax: (781) 828-5365

Web: www.sikacorp.com Email: webmaster.sarnafil@us.sika.com

Canada Office

Sika Sarnafil A Business Unit of Sika Canada 6820 Davand Drive Mississauga, ON L5T 1J5

Tel.: (905) 670-2222 1-800-268-0479 Fax: (905) 670-5278 Web: www.sika.ca

Disclaimer: The information, and, in particular, the recommendation relating to the application and end-use of Sika Sarnafil products, are given in good faith based on Sika Sarnafil's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika Sarnafil recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, may be inferred from this information. The user of the product must determine the product's suitability for the intended application and purpose. Sika Sarnafil reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.